



Typical Properties of Grafil 37-800 30K Carbon Fiber

Fiber Type	Number of Filaments	Strength Ksi (MPa)	Modulus Msi (GPa)	Density lb/in ³ (g/cm ³)	Yield yds/lb (mg/m)	Denier (tex)	X-Sectional Area in ² (mm ²)	Elongation %	Filament Diameter μ m
37-800	30,000	770 (5.30)	36 (250)	0.0657 (1.82)	310 (1,600)	14,400 (1,600)	1.36x10 ⁻³ (0.879)	2.1	6
37-800WD	30,000	770 (5.30)	36 (250)	0.0657 (1.82)	310 (1,600)	14,400 (1,600)	1.36x10 ⁻³ (0.879)	2.1	6

5900 88th Street
 Sacramento, CA
 95828, USA
 Tel: 916.386.1733
 Fax: 916.383.7668
 Web: www.grafil.com



ISO 9001:2008
 FM 56416

03/2011

6, Orchard Court
 Binley Business Park
 Harry Weston Road
 Binley, Coventry CV3 2TQ UK
 Tel: +44 (0) 2476 447272
 Fax: +44 (0) 2476 449565