



PYROFIL™ HS40 12K

Typical Fiber Properties

Tow Tensile	Strength	670 4,610	ksi MPa	JISR 7601
	Modulus	66 455	msi GPa	
Typical Density		0.067 1.85	lb.in ³ g/cm ³	JISR 7601
Typical Yield	12K	1155 430	yds/lb mg/m	JISR 7601

5900 88th Street
 Sacramento, CA
 95828, USA
 Tel: 916.386.1733
 Fax: 916.383.7668
 Web: www.grafil.com



ISO 9001:2008
 FM 56416

03/2010

6, Orchard Court
 Binley Business Park
 Harry Weston Road
 Binley, Coventry CV3 2TQ UK
 Tel: +44 (0) 2476 447272
 Fax: +44 (0) 2476 449565