



PYROFIL™ MR60H 24K

Typical Fiber Properties

Tow Tensile	Strength	825 5,680	ksi MPa	JISR 7601
	Modulus	42 290	msi GPa	
Typical Density		0.065 1.81	lb.in ³ g/cm ³	JISR 7601
Typical Yield	24K	517 960	yds/lb mg/m	JISR 7601

5900 88th Street
 Sacramento, CA
 95828, USA
 Tel: 916.386.1733
 Fax: 916.383.7668
 Web: www.grafil.com



ISO 9001:2008
 FM 56416

03/2010

6, Orchard Court
 Binley Business Park
 Harry Weston Road
 Binley, Coventry CV3 2TQ UK
 Tel: +44 (0) 2476 447272
 Fax: +44 (0) 2476 449565