



PYROFIL™ MS40 12K

Typical Fiber Properties

| | | | | |
|------------------------|----------|---------------|---|-----------|
| Tow Tensile | Strength | 640 4,410 | ksi MPa | JISR 7601 |
| | Modulus | 50 345 | msi GPa | |
| Typical Density | | 0.064 1.77 | lb.in ³ g/cm ³ | JISR 7601 |
| Typical Yield | 12K | 825 600 | yds/lb mg/m | JISR 7601 |

5900 88th Street
 Sacramento, CA
 95828, USA
 Tel: 916.386.1733
 Fax: 916.383.7668
 Web: www.grafil.com



ISO 9001:2000
 FM 56416

07/2008

6, Orchard Court
 Binley Business Park
 Harry Weston Road
 Binley, Coventry CV3 2TQ UK
 Tel: +44 (0) 2476 447272
 Fax: +44 (0) 2476 449565