



# PYROFIL™ TR50S 6K

## Typical Fiber Properties

Tow Tensile	Strength	711 4,900	ksi MPa	ASTM D4018
	Modulus	34 235	msi GPa	
Typical Density		0.066 1.82	lb.in <sup>3</sup> g/cm <sup>3</sup>	ASTM D4018
Typical Yield	6K	1,240 400	yds/lb mg/m	ASTM D4018

5900 88th Street  
 Sacramento, CA  
 95828, USA  
 Tel: 916.386.1733  
 Fax: 916.383.7668  
 Web: www.grafil.com



ISO 9001:2008  
 FM 56416

03/2010

6, Orchard Court  
 Binley Business Park  
 Harry Weston Road  
 Binley, Coventry CV3 2TQ UK  
 Tel: +44 (0) 2476 447272  
 Fax: +44 (0) 2476 449565