



# PYROFIL™ TRH50 12K

## Typical Fiber Properties

Tow Tensile	Strength	710 4,900	ksi MPa	JISR 7601
	Modulus	37 255	msi GPa	
Typical Density		0.065 1.81	lb.in <sup>3</sup> g/cm <sup>3</sup>	JISR 7601
Typical Yield	12K	620 800	yds/lb mg/m	JISR 7601

5900 88th Street  
Sacramento, CA  
95828, USA  
Tel: 916.386.1733  
Fax: 916.383.7668  
Web: [www.grafil.com](http://www.grafil.com)



ISO 9001:2008  
FM 56416

03/2010

6, Orchard Court  
Binley Business Park  
Harry Weston Road  
Binley, Coventry CV3 2TQ UK  
Tel: +44 (0) 2476 447272  
Fax: +44 (0) 2476 449565