



PYROFIL™ TRH50 18K

Typical Fiber Properties

Tow Tensile	Strength	770 5,300	ksi MPa	ASTM D4018
	Modulus	36 250	msi GPa	
Typical Density		0.066 1.82	lb.in ³ g/cm ³	ASTM D4018
Typical Yield	18K	496 1,000	yds/lb mg/m	ASTM D4018

5900 88th Street
 Sacramento, CA
 95828, USA
Tel: 916.386.1733
Fax: 916.383.7668
Web: www.grafil.com



ISO 9001:2008
 FM 56416

03/2010

6, Orchard Court
 Binley Business Park
 Harry Weston Road
 Binley, Coventry CV3 2TQ UK
Tel: +44 (0) 2476 447272
Fax: +44 (0) 2476 449565