



Grafil/Pyrofil Typical Thermal Properties

Fiber	Coefficient Thermal Expansion (10^{-6} m/m/K)	Specific Heat (J/gK)	Thermal Conductivity (W/mK)
Grafil 34-700	0.5	0.74	7
Grafil 34-600	0.5	0.74	7
Pyrofil TR30S	0.5	0.74	7
Pyrofil TR50S	0.5	0.74	7
Pyrofil TRH50	0.5	0.74	7
Pyrofil MR40	0.1	0.73	20
Pyrofil MR60H	0.1	0.73	20
Pyrofil MS40	0.1	0.73	20
Pyrofil HR40	-0.4	0.75	45
Pyrofil HS40	-0.5	0.73	52

5900 88th Street
Sacramento, CA
95828, USA
Tel: 916.386.1733
Fax: 916.383.7668
Web: www.grafil.com



ISO 9001:2008
FM 56416

03/2010

6, Orchard Court
Binley Business Park
Harry Weston Road
Binley, Coventry CV3 2TQ UK
Tel: +44 (0) 2476 447272
Fax: +44 (0) 2476 449565